

Synthetic Leather Limonta Coverlim 11

Price: **€0.00**

Excl. Tax: €0.00

Sku: COVERLIM

Synthetic leather (also known as leatherette) in **140-cm roll heigth** which looks like nappa leather or soft calf and is particularly suitable to make shoes, leather goods, tapestry, car interiors, photo albums, covered buttons and fancy goods in general.

Thickness: **0,5 mm**

Price per length meter (= 1,4 square meters)

Details:

Leatherette Limonta Coverlim 11 - 140 cm high roll

A useful product for those operations which require a specific natural leather that is difficult to find because of its colour or necessary minimum quantity.

Furthermore, synthetic leather may replace natural leather if it is too much expensive for the kind of product someone wants to make.

Immediately available colours in stock: minimum order quantity: **1** linear **meter**. The indicated price refers to one linear meter, which corresponds to 1.40 square metres.

Colours on order: minimum order quantity 20 linear meters. The 20-metre roll price is that which appears by selecting the specific colour option.

TECHNICAL DATA SHEET
Composition: 55% COTTON + 45% POLYURETHANE
Weight in grams per linear metre: 364 +- 21
Weight in grams per square metre: 260 +-17
Thickness mm/100: 56 +-5
Height cm: 137/140

Maintenance instructions: Lavaggio acqua 30° - Lavaggio a secco - Do NOT iron - NO asciugatura - NO candeggio

Test	Regulation	Value	Tolerance	Light - Medium - Dark
Peak longitudinal force	Limonta regulation No. N042/01	43.00 per N/50 mm	-4.30	
Peak longitudinal force extension	Limonta regulation No. N042/01	7.00%	-0.70	
Maximum lateral force	Limonta regulation No. N042/01	3.00 per N/50 mm	-3.80	
Maximum lateral force extension	Limonta regulation No. N042/01	20.00%		
Longitudinal tear resistance	Limonta regulation No. N042/07	3.00 per N	-2.00	
Lateral tear resistance	Limonta regulation No. N042/07	3.00 per N	-0.30	
Abrasion (mart.) 12Kpa	U.E.I. 12947-1-2/00	50,000.00 no. cycles	-0.30	
Curves (Bally) + 20°C	UNI 4818-13°/92	100,000.00 curves		
Colour fastness to dry-cleaning - Bleeding	Limonta regulation No. N021/07			4/5 - 4 - 4
Colour fastness to dry-cleaning - Fading	Limonta regulation No. N021/07			4/5 - 4/5 - 4/5
Colour fastness to water washing - Bleeding	Limonta regulation No. N021/07			4/5 - 4 - 4
Colour fastness to water washing - Fading	Limonta regulation No. N021/07			4-4-4
Colour fastness to light	UNI EN ISO 105-B02/04			4-4-4
Colour fastness to acid sweat - Bleeding	UNI EN ISO 105-E04/98			4/5 - 4/5 - 4
Colour fastness to acid sweat - Fading	UNI EN ISO 105-E04/98			4/5 - 4/5 - 4/5
Colour fastness to basic sweat - Bleeding	UNI EN ISO 105-E04/98			4/5 - 4/5 - 4
Colour fastness to basic sweat - Fading	UNI EN ISO 105-E04/98			4/5 - 4/5 - 4/5
Colour fastness to dry rubbing	UNI EN ISO 105-X12/03			nd - 4/5 - 4/5
Colour fastness to wet rubbing	UNI EN ISO 105-X12/03			nd - 4 - 4
Colour fastness to water - Bleeding	UNI EN ISO 105-E01/98			nd - 4/5 - 4/5

Colour fastness to water - Fading	UNI EN ISO 105-E01/98			nd - 4/5 - 4/5
Stab: Washing in water. 30°C Long.	Limonta regulation No. N048/05	6.00- %	+- 1.00	
Stab: Washing in water. 30°C Lat.	Limonta regulation No. N048/05	3.00- %	+- 1.00	